

ARCHITECTURAL COLLECTION

MI Series

MADISON

Porcelain Stoneware
EN14411 Annexe G - BI a





MI-521
Anthracite




MI-522
Beige





MI-523
Brown




MI-524
Grey




60x120cm



100x100cm



60x60cm



30x60cm



Natural

Slip Resistance		
	R10	+36

Anti-Slip (20mm)

Slip Resistance		
	R11	
	+36	

Available Finishes

Natural : MI-52*.N

Anti-Slip : MI-52*.AS



Madison Anthracite



Madison Beige



Madison Grey



Madison Brown

		Norm Standards	Test Results
	Product Classification	UNI EN 14411	Porcelain Stoneware EN14411 Annexe G Group BIa
	Dimensional and surface quality	UNI EN ISO 10545-2	Complies
	Water absorption	UNE-EN-ISO 10545-3	<=00.5%
	Flexural strength	UNI EN ISO 10545-4	>45N/mm2
	Frost resistance	UNI EN ISO 10545-12	Resistant
	Resistance to acids and alkalis (except hydrofluoric acid)	UNI EN ISO 10545-13	Complies
	Wear and abrasion resistance	UNI EN ISO 10545-6	<140mm3
	Thermal shock resistance	UNI EN ISO 10545-9	Resistant
	Slip resistance	UNE 41901:2017 EX DIN 51130 DIN 51097 BS7976 (PTV) WET ANSI A326.3	Natural R10 PTV +36 Shod Anti-Slip R11 PTV +36 Barefoot
	Colour resistance to sunlight exposure	DIN 51094	No change of colours
	Stain resistance	UNI EN ISO 10545-14	>= Classe 5

Size	Finish	Thickness	Internal Walls	External Walls	Internal Floors	External Floors	Frostproof	Colour Variation	Packing				
									Pcs / Ctn	M² / Ctn	Kg / Ctn	Ctns / Pallet	M² / Pallet
30x60cm	Natural	8mm	•	•	•		Yes	V3	8	1.44	24.96	40	57.6
60x60cm	Natural	8mm	•	•	•		Yes	V3	4	1.44	25.07	32	46.08
100x100cm	Natural	6mm	•	•	•		Yes	V3	2	2	28.12	26	52
60x120cm	Natural	8mm	•	•	•		Yes	V3	2	1.44	25.62	36	51.84
60x60cm	Anti-Slip	20mm			•	•	Yes	V3	2	0.72	35.57	30	21.6
100x100cm	Anti-Slip	20mm			•	•	Yes	V3	1	1	45.5	24	24
60x120cm	Anti-Slip	20mm			•	•	Yes	V3	1	0.72	32.42	32	23.04



 01422 377123

 www.waxmanarchitectural.co.uk

 info@waxmanceramics.co.uk

 **Waxman Ceramics**
Grove Mills
Elland
West Yorkshire
HX5 9DZ

The information contained within this document is, to the best of our knowledge, accurate at the time of production.

We reserve the right to modify this document at any time.

Whilst every attempt has been made to accurately reproduce colours and textures, images used within this document are only intended as a guide.

Please refer to actual product samples before specifying or ordering.